

## 7600 Air-Dry VOC Clear

## ACCELERO

## **Description:**

Accelero 7600 is a VOC compliant Air-Dry Clearcoat with premium finishing properties. It is recommended for high performance bodyshops focusing on efficiency, space utilization and cost reduction with no compromise on premium quality. It can be simply flattened and polished after 1 hour at application temperature.

It uses the existing L.E Hardeners (H820, H920) as other VOC clearcoats in the GENERAL range, providing a complete and compact offer.

## Suitable Substrates:

- "General" GenRock Basecoat.
- "General" Gen<sub>2</sub>O Basecoat.



Mix 2:1 with H820, H920 General Hardeners		
100%	50%	
7600	H820 FAST UHS HARDENER	
7600	H920 SLOW UHS HARDENER	











1 light + 1 full coat
No flash-off between coats
35 – 45 micron
2.0 - 2.2 bar inlet pressure

HVLP 1.2 – 1.3 mm

17-19 s / DIN 4 mm / 20°C Potlife: 60 minutes at 20°C

2.0 2.2 but milet pressure			
Dust free after	15 minutes @ 25 °C (77°F) 30 minutes @ 20 °C (68°F)		
Touch free after	20 minutes @ 25 °C (77°F) 45 minutes @ 20 °C (68°F)		
Sandable & Polishable after	60 minutes @ 25 °C (77°F) 90 minutes @ 20 °C (68°F)		







5 Minutes at 60°C (140 °F) Panel Temperature.

|--|

5-7 minutes, depending on color.
Substrate temperature 80°C-100°C (176°F to 212°F)
\*Important note: keep panel at greater than 80cm from IR unit, depending on repair film thickness.



Wear suitable protection

VOC (2004/42/EC):	VOC (2004/42/EC): 2004/42/EC IIB (d) (420)420. The EU limit value for this product (product category IIB. d) in ready to use form is max 420g/ltr. The VOC content of this product in ready for use form is max. 420 g/l.	
Specific Gravity:	0.997 kg/cm3	+
Flash Point:	25°C (77°F)	
Solids Content:	Approximately 56% by weight RFU	
<b>Coverage:</b>	7-8 m <sup>2</sup> /l at 35-45 micron film thickness (theoretical)	L
SDS:	Refer to the safety data sheet	